



FAST BARANEK stucco mineral plaster work

APPLICATION **FAST BARANEK** is designed for manual making of stucco, thin-coat plaster work both inside as well as outside the building. It can be applied on any mineral base which is adequately fast and even (cement plasters, cement-lime plasters, concrete, the external coat in the insulation systems).

CHARACTERISTICS **FAST BARANEK** is a dry mineral mixture with the addition of the selected quartz aggregate as well as softening agents making the application of the plaster easier and improving the adherence of the plaster to the base. It is characteristic for its high permeability and resistance to water after a complete setting.

PREPARATION OF The base must be even, fast and dry, without any impurities decreasing its adherence such as dust, lime, or remains of previous paint coats. In order to decrease the absorptivity the base should be primed with one of the primes of **FAST**. Always in order to increase the plaster adherence, no matter of what type the base is, it should be primed with **FAST GRUNT M**.

INSTRUCTIONS All the contents of the bag must be stirred mechanically with 5 liters of clean water until an even paste of the intended consistence is reached. **Then, leave it for approximately 10 minutes and stir again**, it must be used up within 1 hour.

Apply a thin, grain-thick coat of plaster with a stainless steel trowel onto a previously, adequately prepared and primed base. Then, after a short while, depending on the conditions during plastering, we can proceed to make patterns with a plastic float, roller, brush or any similar tool. The plaster should be float finished (floated) with circular movements. When plastering, follow the general principle of applying "wet on wet". In case the paste gets thick, stir it again carefully without adding any water. Tools and the container must be clean.

Also, when plastering, be careful about the right weather conditions, which means, avoid great insolation, rain and too much humidity. The temperature should be from + 5° C up to 25° C. The time for the coat to dry up is from 12 to 36 hours.

The plaster can then be coated with acrylic paints not earlier than 4 weeks following plastering, whereas in case of silicate paints, you can proceed with coating after the plaster dries up.

EFFICIENCY Approximately **2,25 kg/m² at the grain thickness of 2,00 mm**
3,00 kg/m² at the grain thickness of 2,50 mm
3,85 kg/m² at the grain thickness of 3,00 mm

STORAGE Store in a manufacture (originally) closed packages in a dry room on pallets at the temperature of +5°C up to 25°C.
Suitability for use: 12 months.



FAST BARANEK stucco mineral plaster work

TECHNICAL SPECIFICATIONS

Mixture proportions	5,00 up to 5,50 litre for 25 kg of the dry substance
Dry substance thickness	1,50 kg/dm³
Readiness for use	approximately 1 hour
Open time:	appr. 20 min
Adherence	min. 0,30 MPa
Air and base temperature:	from +5°C up to +25°C
Temperature resistance	from -20°C up to +60°C

PACKAGES

Bags of 25kg
Pallets: 1050 kg in 25 kg bags (42 bags each)

STANDARDS / NORMS

Technical Approvals ITB – AC 020: AT-15-3513/2005, AT-15-6141/2005
Sanitary Certificate issued by the State Sanitary Department no HK/B/0595/02/2003.

NOTE

The range of the product use recommended and defined in these instructions does not relieve the user/contractor from the obligation of carrying out works following both building principles as well as labour safety regulations. P.W. FAST guarantees and shall be liable for the product quality, however it cannot control methods in which the product was used and under what conditions.

Element of insulating systems: FAST SM, FAST W and FAST W-G.