



FAST KORNİK-AKRYL thin-coat, acrylic plaster

- APPLICATION** **FAST KORNİK-AKRYL** is designed for manual making of stucco, thin-coat plaster both inside and outside the building. It can be applied on any mineral plaster base, provided it is adequately fast and even (cement plaster, cement-lime plaster, concrete, a reinforced coat insulated in the **FAST** system).
- CHARACTERISTICS** **FAST KORNİK-AKRYL** is a ready for use product made on the base of acrylic dispersion delivered in a form of a paste. It is characteristic for its high resistance to air pollution, great fastness and washability. It is steam-permeable and hydrophobic. A wide range of colours is offered.
- PREPARATION OF** The base should be even, fast and dry, without any impurities decreasing its adherence such as dust, lime, or remains of previous paint coats. In order to decrease the absorptivity the base should be primed with one of **FAST** products. Always, in order to increase adherence, independently of the base type, before applying the plaster, prime the base with **FAST GRUNT M**.
- INSTRUCTIONS** Before starting to apply the plaster, contents of each package should be mixed with a slow-running drill in order to make the consistence even. In case of dry contents it is allowable to add 100 to 150 g of water. Apply a thin, grain-thick coat of plaster with a stainless steel trowel onto a previously, adequately prepared and primed base. Then, after a short while, depending on the conditions during plastering, we can proceed to make patterns with a plastic float. The plaster should be float finished (floated) in all directions. When plastering, follow the general principle of applying "wet on wet". The tools and the container must be clean. Also, when plastering, be careful about the right weather conditions, which means, avoid great insolation, rain and too much humidity. The temperature should be from + 5° C up to 25° C. The time for the coat to dry up is from 12 to 48 hours.
Materials bearing different production numbers should be mixed together in order to avoid a difference in colour shades.
- EFFICIENCY** approximately **2,80 kg/m²** at the grain thickness of 2 mm.
approximately **3,50 kg/m²** at the grain thickness of 3 mm.
approximately **4,30 kg/m²** at the grain thickness of 4 mm.
- STORAGE** Store in a manufacture (originally) closed packages in a dry room at the temperature of +5°C up to +25°C.
Suitability for use: 12 months.
- TECHNICAL SPECIFICATIONS**
- | | |
|---------------------------|------------------------------------|
| Adherence | min. 0,10 MPa |
| Open time: | appr. 20 min |
| Weight by volume: | 1,60-1,80 kg/dm³ |
| Air and base temperature: | from +5oC up to +25oC |



FAST KORNİK-AKRYL thin-coat, acrylic plaster

PACKAGES

Plastic buckets of 15 kg.
Pallets of 660 kg in 15 kg buckets (44 items)

STANDARDS / NORMS

Technical Approval ITB – AC 020: AT-15-3513/2005
Sanitary Certificate issued by the State Sanitary Department no HK/B/1755/01/2003.

NOTE

The range of the product use recommended and defined in these instructions does not relieve the user/contractor from the obligation of carrying out works following both building principles as well as labour safety regulations.
P.W. FAST guarantees and shall be liable for the product quality, however it cannot control methods in which the product was used and under what conditions.