



## **FAST ZT** repair and finishing plaster

**APPLICATION** **FAST ZT** is a ready for use plaster designed for construction works as well as repair and finishing works— especially for laying bricks for walls both inside as well as outside buildings. Owing to specially selected components it can be used for making rough coat under plaster work as well as for floating coat.

**CHARACTERISTICS** **FAST ZT** is a ready for use dry mix of mineral elements and improving agents. The universal plaster **FAST ZT** can be applied both inside as well as outside buildings, it is frost- and water-resistant, easy to apply, highly valued for its great adherence and plasticity.

**PREPARATION OF** **FAST ZT** plaster is designed for all bases made of bricks, hollow clay bricks, concrete, chip-cement boards, as well as gypsum and gypsum-concrete surfaces. The base should be free from any impurities such as dust, grease, and bitumens, the remains of old coats, etc. Any old dusting coats that might lower the adherence of the plaster must be removed. Before starting to plaster, moisture the surface with water.

**INSTRUCTIONS** Pour the contents of the sack into 5,0 – 7,5 l of clean water and stir thoroughly with a slow-running drill or manually, until obtaining a desired, uniform consistence without any pellets. The plaster prepared in this way must be applied onto a previously prepared base with a trowel. Remove the excess with a foamed polystyrene or wooden float. Float finish the plaster before it dries up excessively. This work should be done at the air and base temperature of from + 5°C to + 25°C.

**EFFICIENCY** The average use of the plaster is approximately 25 kg / 1,20 – 1,60 m<sup>2</sup> with the thickness of the coat of 10 mm.

**STORAGE** Store in a manufacture (originally) closed packages in a dry room on pallets at the temperature of +5°C up to +25°C.  
Suitability for use: 12 months.

<b>TECHNICAL SPECIFICATIONS</b>	Mixture proportions (rough coat)	<b>appr. 6,50 – 7,50 l of water</b>	<b>per 25kg of the plaster</b>
	Readiness for use	<b>appr. 5,0-6,0 l</b>	
	Mortar class	<b>approximately 4 hours</b>	
	Air and base temperature	<b>M4</b>	
		<b>from +5°C up to +25°C</b>	

**PACKAGES** Bags of 25kg  
Pallets: 1050 kg in 25 kg bags (42 bags)

**STANDARDS /NORMS** Manufactured in accordance with the Polish Norm: PN-B-10109:1998

**NOTE** The product contains cement. In case of eye contact, rinse the affected eye with water and see the doctor.

The range of the product use recommended and defined in these instructions does not relieve the user/contractor from the obligation of carrying out works following both building principles as well as labour safety regulations.  
P.W. FAST guarantees and shall be liable for the product quality, however it cannot control methods in which the product was used and under what conditions.